

PARACIER G

PRODUCT DESCRIPTION AND USES

High performance reinforced SBS elastomeric bitumen membrane self-finished by coloured mineral granules, for waterproofing works.

This product is used as a top layer of 2 layers self-protected systems for non-accessible roof or technical roof on steel sheet.

This product must be used in accordance with the relevant technical specifications (DTA PARACIER FM).

COMPOSITION

Surface	Coloured mineral
Blend	Fillerized SBS (Styrene - Butadiene - Styrene) elastomeric bitumen
Reinforcement	Glassfiber nonwoven 55 g/m ²
Under face	Hot melt film


DIMENSIONAL CHARACTERISTICS

	Slate 6 m	Slate 10 m	Granule 6 m	Granule 10 m
Roll nominal length (m)	6.00	10.00	6.00	10.00
Nominal thickness (mm)	2.6	2.6	2.65	2.6
Nominal width (mm)	1000	1000	1000	1000
Longitudinal selvedge nominal width (mm)	70	70	70	70
Area density (kg/m ²)	4.278	4.278	4.090	4.090
Mass per roll (kg)	25.3	42.2	25.5	42.5

PERFORMANCES

Test	Standard	Unit	Average value
Tensile strength	EN 12 311-1	N/ 50mm	350 x 200
Elongation	EN 12 311-1	%	2.5 x 2.0
Nail tearing resistance	EN12310-1	N	85 x 85
Cold bending temperature	EN 1109	°C	- 20
Heat flow test	EN 1110	°C	100
Waterproofing	EN 1928	-	Pass

ISO 9001 REFERENCE DOCUMENT

<p>Our products are manufactured by certified ISO 9001 plants</p>	
---	---

PACKAGING

	Slate 6 m	Slate 10 m	Granule 6 m	Granule 10 m
Rolls quantity per truck pallet	40	24	40	24
Rolls quantity per container pallet	42	27	42	27
Rolls quantity per wooden box	42	25	42	25

GENERALITIES ABOUT APPLICATION

Using	The generalities about the product using are set out in the ZSA STANDARD
Application	The generalities about the product application are set out in the ZTA STANDARD
Overlaps	Current building practices concerning overlaps are set out in the ZRA STANDARD
Slopes	Current building practices concerning slopes are set out in the ZPA STANDARD

COMPLEMENTARY INFORMATIONS

Values	Where 2 values for given characteristics are shown, the first is for longitudinal direction and the second is for the cross direction.
Tolerances	The average values derived from standard tests and are subject to the usual production variations. Some slight variations can be noticed as the values are based on the average values obtained from several plants.
Modification(s)	Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the up-date technical data sheet, please contact our technical department
Hazardous classification	It is not classified as dangerous according to the international regulation (ADR, RID, IATA, and RTMDR)
Complementary information	This document is only a product technical data sheet, regarding each waterproofing design, please, consult the concerned technical agreement and in case of doubt contact our technical department.
Storage	This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.