

Product Technical Information EXP/056

Rev. 08 - 31/03/2020

PARADIENE BDS

PRODUCT DESCRIPTION AND USES

Reinforced SBS elastomeric bitumen membrane for waterproofing works.

This product is for use as:

- base layer of a two-layers system self-protected or under heavy protection,
- base layer of a two-layer, self-protected roof waterproofing system,
- an underlayer or top layer of a two-layer roof waterproofing system under heavy protection (gravel ballast, slabs on adjustable supports, etc.),
- > vapour barrier on concrete or wooden deck.
- > for miscellaneous works.

In either case, this product must be used in accordance with the relevant technical specifications accepted by our company.

COMPOSITION

| Surface | Sanded |
|---------------|--|
| Blend | Fillerized SBS (Styrene-Butadiene-Styrene) elastomeric bitumen |
| Reinforcement | Glassfiber nonwoven 55 g/m² |
| Underface | Hot melt film |

DIMENSIONAL CHARACTERISTICS

| | 10 m | 7.5 m |
|-------------------------|-------|-------|
| Roll nominal length (m) | 10.00 | 7.50 |
| Nominal thickness (mm) | 2.6 | 2.6 |
| Nominal width (mm) | 1000 | 1000 |
| Area density (kg/m²) | 3.395 | 3.400 |
| Mass per roll (kg) | 34.0 | 25.6 |

PERFORMANCES

| Test | Standard | Unit | Average value |
|-------------------------------|------------------|---------|---------------|
| Tensile strength | EN 12 311-1 | N/ 50mm | 350 x 200 |
| | ASTM D 5147 - 6 | kN/m | 6.6 x 4.4 |
| Elongation | EN 12 311-1 | % | 2.5 x 2.0 |
| | ASTM D 5147 - 6 | % | 4 x 3.3 |
| Nail tearing resistance | EN 12310-1 | Ν | 160×160 |
| Col bending temperature | EN 1109 | °C | -20 |
| Corperiding terriperature | ASTM D 5147 -11 | °C | ≤-20 |
| Heat flow test | EN 1110 | °C | 100 |
| | ASTM D 5147 - 15 | °C | ≥100 |
| Static puncturing resistance | EN 12730 | Kg | < 5 |
| Dynamic puncturing resistance | EN 12691 | mm | 700 |



Product Technical Information EXP/056

Rev. 08 - 31/03/2020

ISO 9001 REFERENCE DOCUMENT



Our products are manufactured by certified ISO 9001 plants

PACKAGING

| | 10 m | 7.5 m |
|-------------------------------------|------|-------|
| Rolls quantity per truck pallet | 30 | 40 |
| Rolls quantity per container pallet | 30 | 48 |
| Rolls quantity per wooden box | 30 | 42 |

GENERALITIES ABOUT APPLICATION

| Using | The generalities about the product using are set out in the ZSA STANDARD |
|-------------|--|
| Application | The generalities about the product application are set out in the ZTA STANDARD |
| Overlaps | Current building practices concerning overlaps are set out in the ZRA STANDARD |
| Slopes | Current building practices concerning slopes are set out in the ZPA STANDARD |

COMPLEMENTARY INFORMATIONS

| Values | Where 2 values for given characteristics are shown, the first is for longitudinal direction and the second is for the cross direction. |
|---------------------------|--|
| Tolerances | The average values derived from standard tests and are subject to the usual production variations. The indicated average values comply with the UEAtc standard and project prEN 13707. The nominal value tolerances comply with the UEAtc standards. Some slight variations can be noticed as the values are based on the average values obtained from several plants. |
| Modification(s) | Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the up-date technical data sheet, please contact our technical department |
| Hazardous classification | It is not classified as dangerous according to the international regulation (ADR, RID, IATA, and RTMDR) |
| Complementary information | This document is only a product technical data sheet, regarding each waterproofing design, please, consult the concerned technical agreement and in case of doubt contact our technical department. |
| Storage | This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources. |