

PRIM'NAP

PRODUCT DESCRIPTION AND USES

High density polyethylene (HDPE) embossed membrane with conical bosses in relief on one side.

This product is used as protection layer on vertical foundation walls before backfilling.

DIMENSIONAL CHARACTERISTICS

	1 x 20 m	1.5 x 20 m	2 x 20 m	2.4 x 20 m	2.4 x 30 m
Width (m)	1.00	1.50	2.00	2.40	2.40
Length (m)	20.0	20.0	20.0	20.0	30.0
Thickness not including excrescence (mm)	0.45	0.45	0.45	0.45	0.45
Conicity (mm)	20	20	20	20	20
Area density (g/m ²)	550	550	550	550	550
Mass per roll (kg)	11.0	16.5	22.0	26.4	39.6

PERFORMANCES

KIND OF TEST	Reference Norm	Units	Average values
Deformation resistance under loading	EN ISO 604	kN/m ²	270
Tensile strength	EN 12311 – 2	N/5 cm	450 x 350
Elongation at break	EN 12311 – 2	%	28 x 26
Tearing resistance	EN 12310 – 1	N	340 x 320

ISO 9001 REFERENCE DOCUMENT


Our products are manufactured by certified ISO 9001 plants

PACKAGING

	1 x 20 m	1,5 x 20 m	2 x 20 m	2,4 x 20 m	2,4 x 30 m
Rolls quantity per truck pallet	24	12	9	12	9
Rolls quantity per container pallet					
Rolls quantity per wooden box					

ASSOCIATED PRODUCTS

PRIM'NAP PROTECTION: High density polyethylene profile with a length of 2 m packaged in bundles of 15 pieces.

PRIM'NAP FIXATIONS: Box of 100 nails of 32 mm with buttons.